

Sample name	Analytes present	Ampulization Details
ASBESTOS IN FRIABLE BULK MATERIAL (not NELAC)	1-2 analytes from the following list: actinolite; amosite; anthophyllite; chrysotile; crocidolite; tremolite	For PLM. Four samples of friable solids containing a variety of asbestos and non-asbestos fiber types. Occasionally a Refractive Index test is substituted for one or two of the bulk samples
ASBESTOS IN NON-FRIABLE BULK MATERIAL (not NELAC)	1-2 analytes from the following list: actinolite; amosite; anthophyllite; chrysotile; crocidolite; tremolite	For TEM. Two samples of non-friable organically bound solids containing a variety of asbestos and non-asbestos fibers